

Fiber8 - OTDR Report 1310 nm

Cable Info

Fiber ID : Fiber8
Location A :
Cable Mfr. : Alcatel CTA
Subset ID :


Cable ID : CTA
Location B :
Type : SM
Color ID :

Link Measurements

Link Loss : 0.503 dB
Link Length : 0.9996 km
Average Loss : 0.504 dB/km

Avg. Splice Loss : ---
Max. Splice Loss : ---
Total ORL : 29.87 dB

OTDR Trace



Marker Info

A : 0.0396 km, 21.126 dB
a : N/A
A to B Distance : 2.3886 km
A to B LSA Loss : 1.166 dB
2-pt. Ev. Loss : 1.197 dB

B : 2.4281 km, 19.929 dB
b : N/A
A to B LSA Att. : 0.488 dB/km

Comments

OTDR -> 2.6km launch cable -> Alcatel fiber test box -> ODI wet-mate -> CTA.
Bare fiber at sea cable end of CTA left unterminated.

Fiber8 - OTDR Report 1550 nm

Cable Info

Fiber ID : Fiber8
Location A :
Cable Mfr. : Alcatel CTA
Subset ID :


Cable ID : CTA
Location B :
Type : SM
Color ID :

Link Measurements

Link Loss : 0.285 dB
Link Length : 0.9999 km
Average Loss : 0.285 dB/km

Avg. Splice Loss : ---
Max. Splice Loss : ---
Total ORL : <19.45 dB

OTDR Trace



Marker Info

A : 0.0396 km, 19.333 dB
a : N/A
A to B Distance : 2.3886 km
A to B LSA Loss : 0.639 dB
2-pt. Ev. Loss : 0.705 dB

B : 2.4281 km, 18.628 dB
b : N/A
A to B LSA Att. : 0.267 dB/km

Comments

coilcord-upper